


EPS Product Chart

Revised January 8, 2010

TYPICAL PROPERTIES AND APPLICATIONS

	Pentane (%WT)	Mean Unexpanded Bead Size (mm)	Recommended Minimum Expanded Density			End-Use Applications
			Single Pass Continuous (PCF)	Double Pass Continuous (PCF)	Batch (PCF)	
MODIFIED						
33MA	6.8	1.40	0.90	0.75	0.90	Insulation, Bean bag, SIP's
33MB	6.1	0.85	1.00	0.80	0.90	Insulation, SIP's, ICF's, Fabricated packaging
33MC	5.4	0.50	1.25	1.00	1.00	Insulation, SIP's, ICF's, Fabricated and Custom packaging
33MAHD	5.3	1.40	1.40	1.00	1.00	Insulation, Board stock
33MBHD	5.1	0.85	1.35	0.90	0.90	Insulation, SIP's, ICF's, Fabricated packaging
35MB	5.1	0.85	1.25	1.00	1.00	Fabricated and Custom packaging
35MC	4.6	0.50	1.25	1.00	1.00	Insulation, SIP's, ICF's, Fabricated Custom packaging
M77A	6.3	1.40	0.90	0.75	0.85	Insulation, Bean bag, SIP's
M77B	6.5	0.85	0.90	0.75	0.90	Insulation, SIP's, Fabricated packaging
M77BHD	5.5	0.85	1.15	0.80	0.90	Insulation, SIP's, Fabricated packaging
M77C	6.2	0.50	1.20	1.00	1.00	Insulation, SIP's, Fabricated packaging/fine surface
*LV MODIFIED						
M77BLV	4.5	0.85	1.20	0.90	0.90	Insulation, SIP's, Fabricated packaging
REGULAR						
34RA	6.3	1.40	1.10	0.90	0.90	Fabricated Packaging
34RB	5.9	0.85	1.20	1.00	1.00	Packaging
34RC	5.4	0.50	1.25	1.00	1.00	Packaging
*LV REGULAR						
34RALV	4.1	1.40	-	-	1.20	High strength / high density >1.25 PCF packaging and produce boxes
34RBLV	3.8	0.85	-	-	1.20	High strength / high density >1.25 PCF packaging and produce boxes
34RCLV	3.6	0.50	-	-	1.40	High strength / high density >1.50 PCF packaging and produce boxes
SPECIALTY						
DYLITE® F271T	5.6	0.40	3.00	-	3.00	Cups and Containers
DYLITE® F271TS	5.6	0.40	3.00	-	3.00	Thin wall packaging
MAKE TO ORDER						
M97C	4.6	0.50	1.50	1.00	1.25	Insulation, SIP's, ICF's, Fabricated packaging
R244C	4.1	0.85	1.40	1.00	1.20	Thermal and regular packaging

*LV - Low Volatile / Low Pentane

 Painesville (one step)

 Beaver Valley (two step)

All information is furnished in good faith, without warranty, representation, inducement or a license of any kind. No guarantee is given that NOVA Chemicals' products will be suitable in purchaser's formulation or processes for any particular end use.

Materials not manufactured by NOVA Chemicals may present hazards in handling and use.