

FPs016-C

Melt Index 0.65

Density 0.916

Features

- Outstanding melt strength
- Superior toughness with excellent tear strength
- Excellent seal properties
- Low gel

Additives

- Process stabilizer
- Polymer process aid

Applications

- Lamination film
- Coextruded sealant layer
- High toughness film

| Properties | | ASTM ⁽¹⁾ | Units | Typical Values ⁽²⁾ |
|--|--------------|---------------------|-------------------|-------------------------------|
| Melt Index⁽³⁾ | | D 1238 | g/10 min | 0.65 |
| Density | | D 792 | g/cm ³ | 0.916 |
| Film Properties⁽⁴⁾ | | | | |
| Thickness | | | µm (mil) | 25 (1.0) |
| Tear Strength | MD | D 1922 | g | 350 |
| | TD | | g | 430 |
| Dart Drop Impact, F₅₀ | | D 1709/A | g | 700 |
| Low Friction Puncture⁽⁵⁾ | | | J/mm (in-lb/mil) | 98 (22) |
| Tensile Strength | MD | D 882 | MPa (psi) | 47 (6 820) |
| | TD | | MPa (psi) | 44 (6 380) |
| Yield Strength | MD | D 882 | MPa (psi) | 8.5 (1 230) |
| | TD | | MPa (psi) | 8.5 (1 230) |
| Elongation | MD | D 882 | % | 470 |
| | TD | | % | 780 |
| 1% Secant Modulus | MD | D 882 | MPa (psi) | 126 (18 270) |
| | TD | | MPa (psi) | 138 (20 020) |
| Haze⁽⁸⁾ | 100% LLDPE | D 1003 | % | 15 |
| | LDPE blended | | % | 7 |
| Gloss @ 45°⁽⁸⁾ | 100% LLDPE | D 2457 | -- | 38 |
| | LDPE blended | | -- | 72 |
| Seal Initiation Temperature @^(5,6,7) | | | °C (°F) | 100 (212) |

(1) Properties designated have been determined using methods which are in accordance with or substantially in accordance with the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190/2.16.

(4) Film properties are typical of blown film extruded on a 2.5" extruder with 4" die and 35-mil die gap at a blow up ratio of 2.5:1, but are dependant upon operating conditions.

(5) NOVA Chemicals test method.

(6) The seal initiation temperature is the temperature at which a 2-mil film achieves a seal strength of 4.4N/13mm.

(7) Tested at 0.5s dwell, 0.27 N/mm² bar pressure, 305mm/min. pull speed.

(8) Typical values obtained with LLDPE/LDPE blends. Intended as guides only; not to be construed as specifications.

FPs016-C sLLDPE

SURPASS®

Availability

SURPASS polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

Storage/Handling

FPs016-C should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. **The NOVA Chemicals Material Safety Data Sheet (MSDS)** contains important safety information and should be reviewed before using the product.

Processing Conditions**Recommended Conditions:**

| | |
|-------------------------|--------------------------------|
| Melt Temperature | 185°C - 220°C 370°F - 430°F |
|-------------------------|--------------------------------|

| | |
|------------------------------|-------------|
| Optimum Blow-up Ratio | 2:1 - 3.5:1 |
|------------------------------|-------------|

| | |
|----------------|--|
| Die Gap | 0.9 mm - 2.1 mm 0.035 in - 0.085 in |
|----------------|--|

| | |
|-----------------------|---------------------------------------|
| Film Thickness | 0.5 mil - 5.0 mil 12.7 µm - 127 µm |
|-----------------------|---------------------------------------|

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

Food Packaging Status

United States: FPs016-C complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 3.2a, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without temperature or food-type restrictions, subject to technical suitability.

Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

Environmental

NOVA Chemicals' polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



LDPE is the SPI resin code developed for low density and linear low density polyethylene to identify material type for sorting and recycling purposes.

www.novachemicals.com

**U.S. Commercial Center
NOVA Chemicals Inc.**
1555 Coraopolis Heights Road
Moon Township, PA 15108
United States of America

Phone - 412.490.4000
Toll Free - 800.222.7213
Fax - 412.490.4155

**European Operating Center
NOVA Chemicals
(International) S.A.**
Avenue de la Gare 12
1700 Fribourg
Switzerland

Phone - 41-26-426-57-57
Fax - 41-26-426-57-70

**Technical Centre
NOVA Chemicals Technical
Centre**
3620 - 32 Street N.E.
Calgary, Alberta
Canada T1Y 6G7

Phone - 403.291.8444
Fax - 403.291.0493

**Head Office
NOVA Chemicals Corporation**
1000 Seventh Avenue S.W.
P.O. Box 2518, Station M
Calgary, Alberta
Canada T2P 5C6

Phone - 403.750.3600
Fax - 403.269.7410

NOVA Chemicals® is a registered trademark of NOVA Brands Ltd; authorized use.

SURPASS® is a registered trademark of NOVA Chemicals Corporation in Canada and of NOVA Chemicals (International) S.A. elsewhere.

The above information is provided in good faith. NOVA Chemicals is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, NOVA CHEMICALS MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.