



RM_s341-U(UG)

Octene Copolymer sHDPE Rotational Molding Resin

PROPERTIES	ASTM ⁽¹⁾	UNITS	TYPICAL VALUES ⁽²⁾
Melt Index ⁽³⁾	D 1238	g/10 min	3.5
Density	D 792	g/cm ³	0.941
ESCR, (F ₅₀) ⁽⁴⁾	D 1693	h	> 1 000
Flexural Modulus ⁽⁵⁾	D 790	MPa (psi)	827 (119 900)
Tensile Yield Strength ⁽⁶⁾	D 638	MPa (psi)	20.2 (2 900)
Elongation at Yield ⁽⁶⁾	D 638	%	12
Melting Point (DSC)		°C (°F)	126 (259)
Heat Distortion Temperature			
- 66 psi (4.64 kg/cm ²)	D 648	°C (°F)	62 (144)
- 264 psi (18.56 kg/cm ²)	D 648	°C (°F)	43 (109)
ARM Low Temperature Impact ⁽⁷⁾			
- 0.125" (3.17 mm)	ARM Method	J (ft-lb)	95 (70)
- 0.250" (6.35 mm)	ARM Method	J (ft-lb)	230 (170)

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/2.16 kg.

(4) Condition A & B, 100% IGEPAL, 50°C, F50 values. From compression molded specimens.

(5) 1% Strain Value. From compression molded samples.

(6) Type IV specimen, 2" (50.8 mm) per minute test speed, 0.075" (1.9 mm) thickness compression molded samples.

(7) -40°C on rotomolded samples

Melt Index 3.5

Density 0.941

FEATURES

- Exceptional low temperature impact properties
- Broad processing window
- Low viscosity for exceptional processability, shorter cycle times, and energy savings
- Superior whiteness for improved part appearance
- Easy mold release
- NSF listed for Standards #24, #51, & #61
- UL 94 HB

ADDITIVES

- Processing antioxidants
- UV stabilizers

APPLICATIONS

- OEM custom and proprietary components
- Recreational and leisure equipment
- Containers, septic tanks and fish boxes
- Large tanks

RMs341-U(UG)

Octene Copolymer sHDPE Rotational Molding Resin

www.novachemicals.com

U.S. Commercial Center

NOVA Chemicals Inc.

1555 Coraopolis Heights Road
Moon Township, PA 15108
United States of America

Phone 412.490.4170
Toll-Free 800.222.7213
Fax 412.490.4083

Technical Centre

NOVA Chemicals Technical Centre

3620 - 32 Street N.E.
Calgary, Alberta
Canada T1Y 6G7

Phone 403.291.8444
Fax 403.291.0493

Head Office

NOVA Chemicals Corporation

1000 Seventh Avenue S.W.
P.O. Box 2518, Station M
Calgary, Alberta
Canada T2P 5C6

Phone 403.750.3600
Fax 403.269.7410

AVAILABILITY

SURPASS polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

STORAGE/HANDLING

RMs341-U(UG) should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Material Safety Data Sheet (MSDS) contains important safety information and should be reviewed before using the product.

PROCESSING CONDITIONS

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

FOOD PACKAGING STATUS

United States: RMs341-U(UG) complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 3.2a, and may thus be used in the United States as an article or component of an article intended for use in contact with food. RMs341-U(UG) is subject to the specific limitation that it may contact food only at temperatures of 212°F and below (21 CFR 176.170(c) Table 2, conditions of use B–H).

Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

RMs341-U(UG) is Certified by NSF to NSF/ANSI Standards #24, #51, and #61. In addition:

- the production facility is audited annually to assure that only authorized materials are used in the product;
- quality assurance and quality control procedures are followed in fabrication, and all the requirements of the standard continue to be met;
- products are sampled and retested on schedule; and
- labeling and product literature are true and accurate with respect to the NSF listed products.

ENVIRONMENTAL

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



is the SPI resin code developed for high density polyethylene to identify material type for sorting and recycling purposes.

 NOVA Chemicals® is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.

SURPASS® is a registered trademark of NOVA Chemicals Corporation in Canada and of NOVA Chemicals (International) S.A. elsewhere; authorized use/utilisation autorisée.

The above information is provided in good faith. NOVA Chemicals is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, NOVA CHEMICALS MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the